



Product Data

LONGTIME PD 2

Issue Number 2 09/11/2004

High Pressure Greases

DESCRIPTION

Optimol Longtime PD are solid free, high pressure greases for long term lubrication with a wide range of applications.

APPLICATION

Castrol Longtime PD additive combination Microflux Trans® adjusts itself to changing loads and actively prevents wear. They can be used for long term or lifetime lubrication even under the most difficult operating conditions such as extreme pressure, vibrations, shock loads and a wide temperature range in highly loaded rolling and sliding bearings. They can also be used in bearings of spinning and grinding spindles, for gear motors exposed to shock loads, in screening and wood shaping machines and for bearing surfaces of printing plates. The temperature application range is -35°C to +140°C

FEATURES BENEFITS

Resistant to cold and hot water

Extraordinary load bearing capacity
Extremely extended operating period even under high loads and optimum wear protection
Smoothing of existing surface damage
Excellent corrosion protection
Extremely extended operating period even under high loads and optimum wear protection
Improvement of the surface quality
Largely prevents fretting corrosion
Easily pumpable in centralised lubricating systems

Resists water wash out





Product Data

LONGTIME PD 2

TYPICAL PHYSICAL CHARACTERISTICS

| | Value | Value | Test Method |
|---|-----------------------|-----------------------|-------------|
| LONGTIME PD | 1 | 2 | - |
| Colour | Brown | Brown | Visual |
| Base | Lithium & mineral oil | Lithium & mineral oil | - |
| Consistency/NLGI Grade | 1 | 2 | DIN 51818 |
| Worked Penetration Pw 60, 0.1mm | 310-340 | 265-295 | DIN ISO2137 |
| Difference: Pw 100.000 - Pw 60, 0.1mm | 12 | 17 | - |
| Density at +20°C g/cm ³ | 0.887 | 0.886 | DIN 51757 |
| Base Oil Viscosity +40°C mm²/s | 93.9 | 94.9 | DIN 51562 |
| Dropping Point, °C | >180 | >180 | DIN ISO2176 |
| Flow Pressure @ -35°C mbar | >1600 | >1600 | DIN 51805 |
| SRV Test Run - test mode 5ae: | | | |
| 300 N50°C/122°F/ball/surface/2hr coefficient of friction wear | | | DIN E 51834 |
| | 0.0683 | 0.070 | |
| ball/scar , mm | 0.55 | 0.55 | |
| profile depth, Pt, μm | 1.0 | 1.40 | |

These technical data are based on average test results. Minor deviations may occur from case to case.

Compatible with all conventional sealing materials and non-ferrous metals

Health and Safety information sheets are available for all Castrol products from the address below: Castrol (U.K.) Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, England, Telephone: Orders/Enquiries (08459)645111, Technical Enquiries (01793)452111, Fax (01793)486083

2 of 2

All reasonable care has been taken to ensure that the information contained in this publication is accurate as at the date of printing. It should be noted however that the information above may be affected by changes occurring subsequent to the date of printing in the blend formulation or methods of application of any of the products referred to or in the requirements of any specification approval relating to any such products.